

technical data sheet for SOFT SOUND™ studio foam

Physical Property	Value	Test Standard
Material	Polyurethane	n/a
Density	1.8 – 2.2 lbs/ft ³	n/a
I.F.D.	@ 25% compression = 40 lbs/min	n/a
Tensile Strength	lbs/in ² = 15 min	n/a
Tear Strength	lbs/in ² = 2 min	n/a
Compression Sets	90%, 22hrs, 158°F	n/a
K-factor @ 30°F	0.23 – 0.28	n/a
Operating Temperature	-40°F to 300°F	n/a
Cell Count	36 – 45 PPI	n/a
Flammability	Passes	UL 94- HF1

The information contained herein is typical and based upon the results of controlled laboratory tests. The information is accurate to the best of American Micro Industries, Inc.'s knowledge. Product performance may vary based on the particular application and installation techniques utilized.